### Get more information on RELICON:

+49 4122 701-5928

www.HellermannTyton.com/RELICON

HellermannTyton is a leading manufacturer and supplier of products for fastening, fixing, installing, connecting, insulating, protecting and identifying electrical cables and data network infrastructure. We also develop parts for customer-specific industrial applications.

Our global brand is trusted by industry professionals around the world. The quality of HellermannTyton products is inspired by your cable management needs.

**RELICON** branded **cast resin and gel systems** extend the HellermannTyton core portfolio with **leading cable connection technology**.

**RELICON** products deliver outstanding performance with **quality you can rely on.** 

## RELICON The Reliable Connection

RELICON is a **HellermannTyton** brand

**HellermannTyton GmbH** · Großer Moorweg 45 · 25436 Tornesch, Germany Tel. +49 4122 701-5928 · RELICON@HellermannTyton.de

# RELICON by HellermannTyton

#### **RELICON Religel Clear**

Transparent and heat-resistant two-component silicone gel





#### **RELICON Religel Clear:**

glossy, transparent gel for perfect visual control.

**RELICON Religel Clear** is a **transparent**, soft elastic two-component silicone gel. It is packed in practical **bottles or canisters including measuring cup** and **mixing stick**.

#### Your benefits

- Optimal visual control through transparent material
- Multiple use possible, mixing ratio 1:1
- Excellent flow and insulating properties
- Excellent moisture and chemical resistance
- Soft elastic, vibration absorbing and removable residue-free

#### **Areas of application**

- LED potting technology
- Encapsulation of printed circuit boards
- Installation of electrical connections
- Belowground or submerged
- Model-making and hobby applications

#### **Tested quality**

- Non-toxic, free of isocyanate
- SVHC-free, contains no hazardous substances.
   The cured product can be disposed of with normal household waste
- Halogen-free













#### **Technical data**



Processing properties		
•	A:B	100:100
Mixing ratio (weight)		
Pot life/Working time	at 23°C	10 min.
Gel time/Polymerisation time	at 23°C	20 min.
Physical characteristics		
Density	0,97 g/cm <sup>3</sup>	DIN EN ISO 2781
Viscosity 23 °C	1075 mPa*s	EN ISO 2555
Expiry date (closed)	no expiry date	
Color (mixed)	glossy-transparent	
Mechanical characteristics (cured)		
Operating temp.	-60 / +200°C	EN ISO 868
Electrical characteristics (cured)		
Dielectric strength 23 °C	25,5 kV/mm	EN ISO 60243-1

Туре	ml	Article-No.
RELICON Religel Clear	500	435-00757
RELICON Religel Clear	1.000	435-00754
RELICON Religel Clear	10.000	435-00755

Non hazardous as per EC Directive 67/548/EEC or 1999/45/EC