



Two-component polyurethane cast resin

RELICON PUR 33

The RELICON PUR 33 cast resin has been created for the electrical insulation and mechanical protection of cable connections in low-voltage electrical networks. Also suitable as mechanical and moisture protection on medium-voltage cable connections.

Application: For indoor and outdoor use.

Features and Benefits

- In a practical, transparent two-chamber pouch
- Colour changes from blue to green whilst mixing
- Safe-Filling system (SF)
- Excellent flow properties, low volume shrinkage
- Cold curing and very hydrophobic, to cast under the influence of water
- High hydrolytic stability and good curing at low temperatures
- UV, ageing and weather resistant
- Outstanding impact strength and resistance to moisture and atmospheric corrosion
- Excellent adhesion to polymeric cables and wires made of PVC, XLPE, PE, EPR
- SVHC-free, contains no hazardous substances, the cured product can be disposed of with house hold waste
- Halogen free



Two-component polyurethane cast resin PUR 33.

MATERIAL	Polyurethane resin 33 (PUR33)
Colour	Green (GN)
Operating Temperature	-25 °C to +120 °C
Mixing Ratio (weight)	100:26
Exothermicity max.	+71 °C
Gel Time	48 min. 5 °C, 20 min. 23 °C, 9 min. 40 °C
Pot Life	43 min. 5 °C, 15 min. 23 °C, 8 min. 40 °C
Dielectric Strength	38 kV/mm
Viscosity	4500 mPa*s, 5 °C (EN ISO 2555), 3000 mPa*s, 23 °C (EN ISO 2555)
Impact Strength	26 kJ/m ²
Shore Hardness D	65±5
Storage Temperature	+4 °C to +40 °C
Shelf Life	48 months

HF ✓

RoHS ✓

TYPE	Resin Quantity	Article-No.
Resin-33-B-SF	95 ml / 130 g	435-00250
	240 ml / 329 g	435-00251
	490 ml / 671 g	435-00252
	655 ml / 897 g	435-00253
	955 ml / 1308 g	435-00254
	1140 ml / 1562 g	435-00255
	1445 ml / 1980 g	435-00256
	1640 ml / 2247 g	435-00257
	1950 ml / 2672 g	435-00258
	2045 ml / 2802 g	435-00259

All dimensions in mm. Subject to technical changes.
Minimum Order Quantity (MOQ) may differ from package content.