Insulation Heat Shrinkable Moulded Shapes



Two-Component Adhesive for Heat Shrinkable Tubing and Shapes

V9500

Features and benefits

- High performance, two-part epoxy adhesive
- · Very resistant to most solvents and fuels, even at elevated temperatures
- Two different packages available
- V9500 available in 10g bags for manual mixing
- Processing set: emery paper, small mixing bowl and wooden spatula
- High performance bonding
- Meets military requirements for heat shrinkable components for harnesses
- VG-approved



V9500 - VG 95343 approved 2K Epoxy Adhesive Kit.



The V9500 applicator gun guarantees the clean and precise coating of special fittings.

MATERIAL	Epoxy resins (EP)	
Colour	Black (BK)	
Curing Temperature	+135 °C	
Curing Time	24 hours at +25 °C, 2 hours at +85 °C	
Operating Temperature	-75 °C to +150 °C	



ТҮРЕ	Description	Designation as per VG-Norm	Tools	Article-No.	
V9500 Epoxy Kit	5 x 10g sachets (50g), 5 x mixing pots, 5 x mixing sticks, 5 x emery papers	VG 95343 T15 A001 A	30	627-95000	
	1 x dual cartridge (50g), 5 x mixing pots, 5 x mixing sticks, 5 x emery papers	VG 95343 T15 A 002 B	30	627-95001	
V9500 Epoxy Cartridge	Two-component adhesive cartridge	VG 95343 T15 D 002 B	30	627-95002	
V9500 Applicator Gun	Applicator gun	VG 95343 T15 DA	-	627-95003	
V9500 Applicator Nozzle	Mixing nozzle	VG 95343 T15 MA	-	627-95004	
All dimensions in mm. Subject to technical changes.					

Recommended Tools 30 H6100 l≞Ì 566

For more information on toolings please refer to the Application Tooling chapter.



www.HellermannTyton.co.uk/V9500-cat22



VG

For product specific approvals and specifications please refer to the Appendix.

