

## Technical data sheet

Article number:  
300-57602

TC20 760



|                                            |                                  |
|--------------------------------------------|----------------------------------|
| <b>Product Group</b>                       | Shrink ratio 2:1 in colours      |
| <b>Product Family</b>                      | Temperature range -55°C to 125°C |
| <b>Material</b>                            | Polyolefin, cross-linked (PO-X)  |
| <b>Colour</b>                              | Red (RD)                         |
| <b>Dielectric Strength</b>                 | 19.7 kV/mm                       |
| <b>Flammability</b>                        | ASTM D2671                       |
| <b>Longitudinal Change After Shrinkage</b> | -15% max.                        |
| <b>Min. Shrink Temperature - °C</b>        | +90 °C                           |
| <b>Operating Temperature</b>               | -55 °C to +125 °C                |
| <b>Package Content packed in</b>           | reel                             |
| <b>Pack Cont.</b>                          | 30 m                             |
| <b>Recov. Ø d max.</b>                     | 38.1 mm                          |
| <b>Shrink Ratio</b>                        | 2:1                              |
| <b>Supplied Ø D min.</b>                   | 76.2 mm                          |
| <b>Wall (WT)</b>                           | 1.27 mm                          |

RoHS