HellermannTyton

Technical data sheet

Article number: 301-10005

SA47 24/6

Product Group	Heat shrinkable tubing 4:1 - 1.2 m lengths
Product Family	SA47 - standard wall adhesive lined
Material	Polyolefin, cross-linked (PO-X)
Colour	Transparent (CL), Black (BK)

Adhesive	Hot melt adhesive
Behaviour at Heat Shock	not cracking
Dielectric Strength [Test method]	20 kV/mm [ASTM D149]
Elongation at break [Test method]	450% [ASTM D2671]
Heat Shock Test	4h/225°C
Longitudinal Change After Shrinkage	-10% max.
Min. Shrink Temperature - °C	+130 °C
Operating Temperature	-40 °C to +125 °C
Package Content packed in	pcs.
Pack Cont.	1.2 m
Recov. Ø d max.	6.00 mm
Shrink Ratio	4:1
Supplied Ø D min.	24.00 mm
Tensile Strength [Test method]	14 MPa [ASTM D2671]
Wall (WT)	2.20 mm
Water Absorption	0.5 %



Technical changes and errors reserved. It's up to the customer to check the suitability for a specific application by means of tests.