HellermannTyton

Technical data sheet

Article number: 301-10010

SA47-HT 7.6/1.7

SA47-HT - standard wall adhesive lined
Polyolefin, cross-linked (PO-X)
Black (BK)
-

Adhesive	Hot melt adhesive
Behaviour at Heat Shock	not cracking
Dielectric Strength [Test method]	20 kV/mm [ASTM D149]
Elongation at break [Test method]	450% [ASTM D2671]
Heat Shock Test	4h/225°C
Longitudinal Change After Shrinkage	-10% max.
Min. Shrink Temperature - °C	+130 °C
Operating Temperature	-40 °C to +150 °C
Package Content packed in	pcs.
Pack Cont.	1.2 m
Recov. Ø d max.	1.70 mm
Shrink Ratio	4:1
Supplied Ø D min.	7.60 mm
Tensile Strength [Test method]	14 MPa [ASTM D2671]
Wall (WT)	1.52 mm
Water Absorption	0.5 %



Technical changes and errors reserved. It's up to the customer to check the suitability for a specific application by means of tests.