

## Technical data sheet

Article number:  
301-10012

SA47-HT 11.6/2.5

Product Group	Heat shrinkable tubing 4:1 - 1.2 m lengths
Product Family	SA47-HT - standard wall adhesive lined
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Adhesive	Hot melt adhesive
Behaviour at Heat Shock	not cracking
Dielectric Strength [Test method]	20 kV/mm [ASTM D149]
Elongation at break [Test method]	450% [ASTM D2671]
Heat Shock Test	4h/225°C
Longitudinal Change After Shrinkage	-10% max.
Min. Shrink Temperature - °C	+130 °C
Operating Temperature	-40 °C to +150 °C
Recov. Ø d max.	2.50 mm
Shrink Ratio	4:1
Supplied Ø D min.	11.60 mm
Tensile Strength [Test method]	14 MPa [ASTM D2671]
Wall (WT)	2.29 mm
Water Absorption	0.5 %

RoHS 