

## Technical data sheet

Article number:  
301-10014

**SA47-HT 32/8**

|  |  |
|--|--|
| <b>Product Group</b>                       | Heat shrinkable tubing 4:1 - 1.2 m lengths |
| <b>Product Family</b>                      | SA47-HT - standard wall adhesive lined     |
| <b>Material</b>                            | Polyolefin, cross-linked (PO-X)            |
| <b>Colour</b>                              | Black (BK)                                 |
|  |  |
| <b>Adhesive</b>                            | Hot melt adhesive                          |
| <b>Behaviour at Heat Shock</b>             | not cracking                               |
| <b>Dielectric Strength [Test method]</b>   | 20 kV/mm [ASTM D149]                       |
| <b>Elongation at break [Test method]</b>   | 450% [ASTM D2671]                          |
| <b>Heat Shock Test</b>                     | 4h/225°C                                   |
| <b>Longitudinal Change After Shrinkage</b> | -10% max.                                  |
| <b>Min. Shrink Temperature - °C</b>        | +130 °C                                    |
| <b>Operating Temperature</b>               | -40 °C to +150 °C                          |
| <b>Package Content packed in</b>           | pcs.                                       |
| <b>Pack Cont.</b>                          | 1.2 m                                      |
| <b>Recov. Ø d max.</b>                     | 8.00 mm                                    |
| <b>Shrink Ratio</b>                        | 4:1  |
| <b>Supplied Ø D min.</b>                   | 32.00 mm                                   |
| <b>Tensile Strength [Test method]</b>      | 14 MPa [ASTM D2671]                        |
| <b>Wall (WT)</b>                           | 2.54 mm                                    |
| <b>Water Absorption</b>                    | 0.5 %                                      |

**RoHS** 