

Technical data sheet

Article number:
305-25419

HFT-B-25.4/12.7



Product Group	Heat Shrinkable Tubing 2:1 flexible and transparent
Product Family	HFT-B - halogen free
Material	Polyolefin, cross-linked (PO-X)
Colour	Transparent (CL)
Dielectric Strength	25 kV/mm
Elongation at break	540%
Heat Shock Elongation	540 %
Heat Shock Tensile Strength	25 MPa
Heat Shock Test	4h/200°C
Insulation Class	B (VDE 0530)
Longitudinal Change After Shrinkage	-5% max.
Min. Shrink Temperature - °C	+135 °C
Operating Temperature	-55 °C to +135 °C
Recov. Ø d max.	12.7 mm
Shrink Ratio	2:1
Specifications	DEF STAN 59-97/3, MIL-DTL-23053/5C, NF F 00-608
Supplied Ø D min.	25.4 mm
Tensile Strength	25 MPa
Wall (WT)	0.90 mm

HF ✓

RoHS ✓

DEF STAN

MIL

NF F