

Technical data sheet

Article number:
308-30421

HIS-3-BAG 4.5/1.5 CL



Product Group	Heat shrinkable tubing 3:1 in blister bags
Product Family	HIS-3 BAG
Material	Polyolefin, cross-linked (PO-X)
Colour	Transparent (CL)
Behaviour at Heat Shock	not fluid, not dripping, not cracking
Behaviour at Low Temperature [Test method]	not cracking [UL 224]
Dielectric Strength [Test method]	32 kV/mm [IEC 60243]
Elongation at break [Test method]	800 [ASTM D2671]
Elongation At Heat Aging	400 %
Heat Aging Test [Test method]	168h/175°C [UL 224]
Heat Shock Test	4h/250°C
Insulation Class	B (VDE 0530)
Longitudinal Change After Shrinkage	+/-5%
Min. Shrink Temperature - °C	+100 °C
Minimum Tensile Strength At Heat Aging	13 MPa
Operating Temperature	-55 °C to +135 °C
Package Content packed in	bag
Pack Cont.	10 pcs.
Shrink Ratio	3:1
Specifications	ANSI/UL 224
Tensile Strength [Test method]	14 MPa [ASTM D2671]
UL-File Number	E143529
Water Absorption	0.15 %

RoHS

CALUS