

Technical data sheet

Article number:
309-21273

TF21-12.7/6.4



Product Group	Heat shrinkable tubing 2:1 - flexible and coloured
Product Family	TF21
Material	Polyolefin, cross-linked (PO-X)
Colour	Orange (OG), High Voltage (HV)
Behaviour at Heat Shock	not refractive, not fluid, not dripping
Behaviour at Low Temperature [Test method]	not cracking [SAE-AS23053]
Dielectric Strength	30 kV/mm
Elongation at break [Test method]	400 % [ASTM D638]
Elongation At Heat Aging	420 %
Flammability	ASTM D876
Heat Aging Test [Test method]	168h/175°C [SAE-AS23053]
Heat Shock Test	4h/250°C
Longitudinal Change After Shrinkage	+/-5%
Min. Shrink Temperature - °C	+90 °C
Operating Temperature	-55 °C to +135 °C
Package Content packed in	pack
Pack Cont.	50 m
Recov. Ø d max.	6.4 mm
Shrink Ratio	2:1
Specifications	ANSI/UL 224, JAR/FAR 25.853
Supplied Ø D min.	12.7 mm
Tensile Strength [Test method]	14 MPa [ASTM D638]
UL-File Number	E143529
UV-Stabilised	No
Wall (WT)	0.64 mm

RoHS 

JAR/FAR 