


## Technical data sheet

Article number:  
309-50243

TF24-2.4/1.2



|                                     |                                                       |
|-------------------------------------|-------------------------------------------------------|
| Product Group                       | Heat shrinkable tubing 2:1 - flexible and transparent |
| Product Family                      | TF24                                                  |
| Material                            | Polyolefin, cross-linked (PO-X)                       |
| Colour                              | Transparent (CL)                                      |
| Behaviour at Heat Shock             | not dripping, not fluid, not cracking                 |
| Behaviour At Low Temperature        | not cracking                                          |
| Dielectric Strength                 | 30 kV/mm                                              |
| Elongation at break (min.)          | 450 %                                                 |
| Elongation At Heat Aging            | 250 %                                                 |
| Heat Aging Test                     | 168h/175°C                                            |
| Heat Shock Test                     | 4h/250°C                                              |
| Longitudinal Change After Shrinkage | +/-5% max.                                            |
| Min. Shrink Temperature - °C        | +110 °C                                               |
| Operating Temperature               | -55 °C to +135 °C                                     |
| Package Content packed in           | reel                                                  |
| Pack Cont.                          | 150 m                                                 |
| Recov. Ø d max.                     | 1.2 mm                                                |
| Shrink Ratio                        | 2:1                                                   |
| Supplied Ø D min.                   | 2.4 mm                                                |
| Tensile Strength                    | 20 MPa                                                |
| Wall (WT)                           | 1.51 mm                                               |
| Water Absorption                    | 0.2 %                                                 |

HF ✓

RoHS ✓