

## Technical data sheet

Article number:  
309-61024

TFN21 12.7/6.4



Product Group	Heat shrinkable tubing 2:1 - flexible and coloured
Product Family	TFN21
Material	Polyolefin, cross-linked (PO-X)
Colour	Transparent (CL)
Behaviour at Heat Shock	not cracking, not breaking, not fluid
Behaviour at Low Temperature [Test method]	not cracking [UL 224]
Dielectric Strength [Test method]	20 kV/mm [ASTM D150]
Elongation at break (min.) [Test method]	600 % [ASTM D2671]
Elongation At Heat Aging	700 %
Heat Aging Test [Test method]	168h/175°C [UL 224]
Heat Shock Test	4h/250°C
Longitudinal Change After Shrinkage	+/-5%
Min. Shrink Temperature - °C	+70 °C
Minimum Tensile Strength At Heat Aging	13.5 MPa
Operating Temperature	-55 °C to +135 °C
Package Content packed in	reel
Pack Cont.	30 m
Recov. Ø d max.	6.4 mm
Shrink Ratio	2:1
Supplied Ø D min.	12.7 mm
Tensile Strength [Test method]	14 MPa [ASTM D2671]
Wall (WT)	0.62 mm

