

Technische datasheet

Artikel Nummer
311-01279

TK20-12.7/6.4



Productgroep	Krimpkous 2:1 uit PVDF
Productfamilie	TK20
Materiaal	Polyvinylidene fluoride (PVDF)
Kleur	transparant (CL)
Brandbaarheid	UL224 VW1
Breekspanning [Testmethode]	≥350% [ASTM D882]
Certificering	UL 224 150 °C 600V VW-1, VG 95343-5:2016-10
Diëlektrische sterkte [Testmethode]	30 kV/mm [SAE-AS23053]
Gebruikstemperatuur - °C	-55 °C tot +175 °C
Hitteschoktest	4h/300°C
Hitteveroudering rek (%)	200 %
Hitteverouderingstest [Testmethode]	168h/250°C [ASTM D638]
Hoeveelheid per	st.
Inhoud	25 st.
Isolatieklasse	F (VDE 0530)
Krimpverhouding	2:1
Lage temperatuur testmethode	SAE-AS23053
Lengtekrimp	+/-10 % max.
Maat bij uitlevering Ø D	12,7 mm
Minimale krimptemperatuur - °C	+170 °C
Na vrije krimp Ø d	6,4 mm
Treksterkte [Testmethode]	40 MPa [ASTM D412]
UL-File nummer	E198023
Wanddikte (WT)	0,30 mm
Waterabsorptie	0,2 %

