

## Technical data sheet

Article number:  
311-20600

TC30 6-2



Product Group	General Purpose Polyolefin tubing
Product Family	Thin wall shrink ratio 3:1
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Dielectric Strength	19.7 kV/mm
Flammability	ASTM D2671
Longitudinal Change After Shrinkage	-15% max.
Min. Shrink Temperature - °C	+90 °C
Operating Temperature	-55 °C to +125 °C
Package Content packed in	reel
Pack Cont.	150 m
Recov. Ø d max.	2.0 mm
Shrink Ratio	3:1
Supplied Ø D min.	6.0 mm
Wall (WT)	0.70 mm

RoHS

