

Technical data sheet

Article number:
315-40640

SR27-6.4/3.2



Product Group	Suitable in smoke sensitive areas
Product Family	Shrink ratio 2:1 a 3:1 version available on request.
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Dielectric Strength [Test method]	19.7 kV/mm [IEC 684 P2]
Longitudinal Change After Shrinkage	+5%/-10% max.
Min. Shrink Temperature - °C	+115 °C
Operating Temperature	-40 °C to +105 °C
Recov. Ø d max.	3.2 mm
Shrink Ratio	2:1
Specifications	DEF STAN 59-97/3
Supplied Ø D min.	6.4 mm
Wall (WT)	0.90 mm

HF ✓

LFH ✓

RoHS ✓

DEF STAN