

Technical data sheet

Article number: 315-50320

TR27-3.2/1.6



Product Group	Heat shrinkable tubing 2:1 - Flame retardant
Product Family	TR27
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Behaviour at Heat Shock	not cracking, not dripping, not fluid
Dielectric Strength [Test method]	15 kV/mm [IEC 684 P2]

Behaviour at Heat Shock	not cracking, not dripping, not fluid
Dielectric Strength [Test method]	15 kV/mm [IEC 684 P2]
Elongation at break	200%
Heat Shock Test	4h/150°C
Longitudinal Change After Shrinkage	+5%/-10% max.
Min. Shrink Temperature - °C	+115 °C
Operating Temperature	-40 °C to +105 °C
Recov. Ø d max.	1.6 mm
Shrink Ratio	2:1
Specifications	EN [45545-2]]
Supplied Ø D min.	3.2 mm
Tensile Strength	7 MPa
Wall (WT)	0.51 mm
Water Absorption	1.0 %



EN 45545-2