


Technical data sheet

Article number:
317-41800

TA40 16/4



Product Group	Heat shrink tubing, adhesive lined - 1.2 m length
Product Family	TA40 thin wall tubing, 4:1 shrink ratio
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Adhesive	Hot melt adhesive
Behaviour at Heat Shock	not cracking, not dripping, not fluid
Behaviour At Low Temperature	not cracking
Dielectric Strength [Test method]	20 kV/mm [ASTM D876]
Elongation at break [Test method]	350% [ASTM D638]
Flammability	ASTM D2671 B
Heat Aging Test [Test method]	168h/175°C [SAE-AS23053]
Heat Shock Test	4h/225°C
Longitudinal Change After Shrinkage	-7% max.
Min. Shrink Temperature - °C	+120 °C
Operating Temperature	-55 °C to +110 °C, (outer wall only)
Recov. Ø d max.	4.0 mm
Shrink Ratio	4:1
Supplied Ø D min.	16.0 mm
Tensile Strength [Test method]	16 MPa [ASTM D638]
Wall (WT)	1.80 mm

