


## **Technical data sheet**

## Article number: 318-50600

TA32-6/2



Product Group	Heat shrinkable tubing adhesive lined - 1.2 m lengths
Product Family	TA32 - thin wall, 3:1 shrink ratio
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)

Adhesive	Hot melt adhesive
Behaviour at Heat Shock	not cracking, not dripping, not fluid
Dielectric Strength [Test method]	25 kV/mm [ASTM D876]
Elongation at break [Test method]	350% [ASTM D638]
Flammability	UL 224 VW-1
Heat Shock Test	4h/250°C
Longitudinal Change After Shrinkage	-15% max.
Min. Shrink Temperature - °C	+110 °C
Operating Temperature	-55 °C to +125 °C
Recov. Ø d max.	2.0 mm
Shrink Ratio	3:1
Specifications	UL 224 125 °C 600V, CSA   C22.2 no. 198.1-99
Supplied Ø D min.	6.4 mm
Tensile Strength [Test method]	15 MPa [ASTM D638]
Wall (WT)	1.20 mm





