


Technical data sheet

Article number:
318-60101

TAN33-4.8



Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Behaviour At Low Temperature	not cracking
Dielectric Strength	20 kV/mm
Elongation at break	3
Longitudinal Change After Shrinkage	+/-10% max
Min. Shrink Temperature - °C	+110 °C
Operating Temperature	-55 °C to +125 °C
Recov. Ø d max.	1.6 mm
Shrink Ratio	3:1
Specifications	CSA
Supplied Ø D min.	4.8 mm
Tensile Strength	12 MPa
Wall (WT)	1.10 mm

RoHS

