


Technical data sheet

Article number:
318-60104

TAN33-12



Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Behaviour At Low Temperature	not cracking
Dielectric Strength	20 kV/mm
Elongation at break	3
Longitudinal Change After Shrinkage	+/-10% max
Min. Shrink Temperature - °C	+110 °C
Operating Temperature	-55 °C to +125 °C
Recov. Ø d max.	4.0 mm
Shrink Ratio	3:1
Specifications	CSA
Supplied Ø D min.	12.0 mm
Tensile Strength	12 MPa
Wall (WT)	1.60 mm

RoHS

