

Technical data sheet

Article number: 319-40000

TREDUX Promo Pack



Product Group	Heat shrinkable tubing up to 3:1 - 1 m lengths
Product Family	TREDUX - thin wall
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Behaviour at Heat Shock	not fluid, not dripping, not cracking
Behaviour at low Temperature test method	UL 224
Dielectric Strength [Test method]	20 kV/mm [IEC 60243]
Elongation at break [Test method]	6 [ASTM D2671]
Elongation At Heat Aging	400 %
Flammability	UL 224 VW-1
Heat Aging Test	168h/175°C
Heat Shock Test	4h/250°C
Insulation Class	B (VDE 0530)
Longitudinal Change After Shrinkage	+/-5%
Min. Shrink Temperature - °C	+70 °C
Minimum Tensile Strength At Heat Aging	11 MPa
Operating Temperature	-55 °C to +135 °C
Package Content packed in	pack
Pack Cont.	1 pc.
Shrink Ratio	2:1 from 38.1/19.1 mm to 101.6/50.8 mm, 3:1 from 1.5/0.5 mm to 24/8 mm
Tensile Strength [Test method]	14 MPa [ASTM D2671]
UL-File Number	E143529
Water Absorption	0.2 %

