

Technical data sheet

Article number:
321-00103

HA40-33/8



Product Group	Heat shrinkable tubing 4:1 - Flame retardant
Product Family	HA40 - thick wall adhesive lined
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Adhesive	Hot melt adhesive
Behaviour at Heat Shock	not cracking
Behaviour at Low Temperature [Test method]	not cracking [ASTM D2671]
Dielectric Strength [Test method]	15 kV/mm [IEC 60243-1]
Elongation at break [Test method]	300 [ASTM D2671]
Elongation At Heat Aging	300 %
Heat Aging Test [Test method]	168h/150°C [ASTM D2671]
Heat Shock Test	4h/225°C
Longitudinal Change After Shrinkage	-10% max.
Min. Shrink Temperature - °C	+120 °C
Minimum Tensile Strength At Heat Aging	12 MPa
Operating Temperature	-55 °C to +110 °C
Package Content packed in	pcs.
Pack Cont.	3 m
Recov. Ø d max.	8.0 mm
Shrink Ratio	up to 4:1
Specifications	DIN EN ISO 8580, DNV
Supplied Ø D min.	33.0 mm
Tensile Strength [Test method]	12 MPa [ASTM D2671]
Wall (WT)	3.20 mm

RoHS ✓

