

Technical data sheet

Article number:
323-00100

MA40-8/2



Product Group	Heat shrinkable tubing 4:1 - Flame retardant
Product Family	MA40 - medium wall adhesive lined
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Adhesive	Hot melt adhesive
Dielectric Strength [Test method]	15 kV/mm [IEC 60243-1]
Elongation at break [Test method]	350 [ASTM D2671]
Elongation At Heat Aging	300 %
Heat Aging Test [Test method]	168h/150°C [ASTM D2671]
Longitudinal Change After Shrinkage	-10% max.
Min. Shrink Temperature - °C	+120 °C
Minimum Tensile Strength At Heat Aging	12 MPa
Operating Temperature	-55 °C to +110 °C
Package Content packed in	lengths
Pack Cont.	10 pcs.
Recov. Ø d max.	2.0 mm
Shrink Ratio	up to 4:1
Supplied Ø D min.	8.0 mm
Tensile Strength [Test method]	12 MPa [ASTM D2671]
Wall (WT)	1.7 mm

