

## Technical data sheet

Article number:  
323-25207

MM30 95/25 1m length



<b>Material</b>	Polyolefin, cross-linked (PO-X)
<b>Colour</b>	Black (BK)
<b>Adhesive</b>	Mastic glue
<b>Behaviour at Heat Shock</b>	not cracking, not fluid, not dripping
<b>Behaviour at Low Temperature [Test method]</b>	not cracking [ASTM D2671]
<b>Dielectric Strength [Test method]</b>	15 kV/mm [IEC 60243]
<b>Elongation at break [Test method]</b>	200 [ASTM D2671]
<b>Elongation At Heat Aging</b>	100 %
<b>Heat Aging Test [Test method]</b>	168h/150°C [ASTM D2671]
<b>Heat Shock Test</b>	4h/225°C
<b>Longitudinal Change After Shrinkage</b>	-10% max.
<b>Min. Shrink Temperature - °C</b>	+120 °C
<b>Minimum Tensile Strength At Heat Aging</b>	8 MPa
<b>Operating Temperature</b>	-40 °C to +120 °C
<b>Package Content packed in</b>	pcs.
<b>Recov. Ø d max.</b>	25.0 mm
<b>Shrink Ratio</b>	up to 5:1
<b>Supplied Ø D min.</b>	95.0 mm
<b>Tensile Strength [Test method]</b>	12 MPa [ASTM D2671]
<b>Wall (WT)</b>	3.6 mm

**RoHS** ✓