

## Technical data sheet

Article number:  
332-03821

KYNAR® 1 1/2



|                                     |                                                          |
|-------------------------------------|----------------------------------------------------------|
| Product Group                       | Heat Shrinkable Tubing 2:1 - PVDF                        |
| Product Family                      | Kynar®                                                   |
| Material                            | Polyvinylidene Fluoride (PVDF)                           |
| Colour                              | Transparent (CL)                                         |
|                                     |                                                          |
| Dielectric Strength [Test method]   | 30 kV/mm [IEC 684 P2]                                    |
| Flammability                        | UL 224 VW-1                                              |
| Insulation Class                    | F (VDE 0530)                                             |
| Longitudinal Change After Shrinkage | -5% max.                                                 |
| Min. Shrink Temperature - °C        | +175 °C                                                  |
| Operating Temperature               | -55 °C to +175 °C                                        |
| Recov. Ø d max.                     | 19.0 mm                                                  |
| Shrink Ratio                        | 2:1                                                      |
| Specifications                      | VG 95343, MIL-DTL-23053/8, UL 224 VW-1, DEF STAN 59-97/3 |
| Supplied Ø D min.                   | 38.0 mm                                                  |
| Wall (WT)                           | 0.51 mm                                                  |

RoHS ✓

DEF STAN MIL VG