

Technische datasheet

Artikel Nummer
333-20902

TF31-9/3



Productgroep	Krimpkous 3:1 flexibel, diverse kleuren
Productfamilie	TF31
Materiaal	Polyolefine vernet (PO-X)
Kleur	rood (RD)
Brandbaarheid	UL224 VW1
Breekspanning [Testmethode]	4% [ASTM D638]
Certificering	ANSI/UL 224, CSA-C22.2 No.198.1-99
Diëlektrische sterkte	30 kV/mm
Gebruikstemperatuur - °C	-55 °C tot +135 °C
Hitteschoktest	4h/250°C
Hitteveroudering rek (%)	400 %
Hitteverouderingstest [Testmethode]	168h/158°C [SAE-AMS-DTL-23053]
Hoeveelheid per	rol
Inhoud	150 m
Krimpverhouding	3:1
Lage temperatuur testmethode	UL 224
Lengtekrimp	+5 % / -15 %
Maat bij uitlevering Ø D	9,0 mm
Minimale krimptemperatuur - °C	+90 °C
Na vrije krimp Ø d	3,0 mm
Treksterkte [Testmethode]	12 MPa [ASTM D638]
UL-File nummer	E143529
Wanddikte (WT)	0,80 mm

