

Technical data sheet

Article number:
340-12040

EPS-300-12/4



Product Group	Heat shrinkable tubing adhesive lined
Product Family	EPS-300 - 3:1 shrink ratio
Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Adhesive	Hot melt adhesive
Behaviour at Low Temperature [Test method]	not cracking [IEC 60684-2]
Dielectric Strength [Test method]	45 kV/mm [IEC 60684-2]
Elongation at break [Test method]	450% [IEC 60684-2]
Heat Shock Elongation	480 %
Heat Shock Tensile Strength	12 MPa
Heat Shock Test	4h/200°C
Longitudinal Change After Shrinkage	-5% max.
Min. Shrink Temperature - °C	+120 °C
Operating Temperature	-55 °C to +125 °C
Package Content packed in	metre
Pack Cont.	100 m
Recov. Ø d max.	4.0 mm
Shrink Ratio	3:1
Supplied Ø D min.	12.0 mm
Tensile Strength [Test method]	14 MPa [IEC 60684-2]
Wall (WT)	1.80 mm

