

Technical data sheet

Article number:
342-11020

PST-HT-6.4/3.2



Product Group	Heat Shrinkable Tubing 2:1 - Elastomer
Product Family	PST-HT - light weight
Material	Elastomer, cross-linked (POA)
Colour	Black (BK)
Dielectric Strength [Test method]	20 kV/mm [IEC 684 P2]
Elongation at break	450%
Elongation At Heat Aging	350 %
Heat Shock Tensile Strength	14
Longitudinal Change After Shrinkage	-10% max.
Min. Shrink Temperature - °C	+135 °C
Operating Temperature	-75 °C to +150 °C
Recov. Ø d max.	3.2 mm
Shrink Ratio	2:1
Specifications	DEF STAN 59-97/3, VG 95343, NF F 00-608
Supplied Ø D min.	6.4 mm
Tensile Strength	17 MPa
Wall (WT)	0.60 mm

RoHS

DEF STAN NF F VG