

Technical data sheet

Article number:
342-29160

PST-H-102.0/51.0



Product Group	Heat Shrinkable Tubing 2:1 - Elastomer
Product Family	PST-H
Material	Elastomer, cross-linked (POA)
Colour	Black (BK)
Behaviour At Low Temperature	not cracking
Dielectric Strength [Test method]	20 kV/mm [IEC 684 P2]
Elongation At Heat Aging	350 %
Heat Shock Elongation	350 %
Heat Shock Tensile Strength	14 MPa
Heat Shock Test	4h/208°C
Longitudinal Change After Shrinkage	-10% max.
Min. Shrink Temperature - °C	+135 °C
Minimum Tensile Strength At Heat Aging	14 MPa
Operating Temperature	-75 °C to +150 °C
Recov. Ø d max.	51.0 mm
Shrink Ratio	2:1
Specifications	DEF STAN 59-97/3, NF F 00-608, LEA, VDE VG 95343-5:2016-10
Supplied Ø D min.	102.0 mm
Wall (WT)	3.50 mm

RoHS

