

Technical data sheet

Article number:
342-33810

PST-HT-38.0/19.0



Product Group	Heat Shrinkable Tubing 2:1 - Elastomer
Product Family	PST-HT - light weight
Material	Elastomer, cross-linked (POA)
Colour	Black (BK)
Dielectric Strength [Test method]	20 kV/mm [IEC 684 P2]
Elongation at break	450%
Elongation At Heat Aging	350 %
Heat Shock Tensile Strength	14
Longitudinal Change After Shrinkage	-10% max.
Min. Shrink Temperature - °C	+135 °C
Operating Temperature	-75 °C to +150 °C
Recov. Ø d max.	19.0 mm
Shrink Ratio	2:1
Specifications	DEF STAN 59-97/3, NF F 00-608, VDE VG 95343-5:2016-10
Supplied Ø D min.	38.0 mm
Tensile Strength	17 MPa
Wall (WT)	1.00 mm

RoHS

DEF STAN NF F VDE VG