

Technical data sheet

Article number:
343-06020

PTA300 6/2

Material	Polyolefin, cross-linked (PO-X)
Colour	Black (BK)
Dielectric Strength [Test method]	15 kV/mm [IEC 684 P2]
Flammability	ASTM D2671 (outer layer only)
Longitudinal Change After Shrinkage	-10% max.
Min. Shrink Temperature - °C	+120 °C
Operating Temperature	-55 °C to +110 °C, (outer wall only)
Package Content packed in	metre
Pack Cont.	300 m
Recov. Ø d max.	2.0 mm
Shrink Ratio	3:1
Supplied Ø D min.	6.0 mm
Wall (WT)	1.00 mm

RoHS 