

Technical data sheet

Article number:
435-01247

Resin-771-SF_N

Product Group	Two-component polyurethane cast resin
Product Family	RELICON PUR 771
Material	Polyurethane resin (PUR)
Colour	Black (BK)
Application Range	Low Voltage
Dielectric Strength	20 kV/mm
Exothermie (max.)	+71 °C
Gel Time	70 min. 5°C, 20 min. 23°C, 8 min. 40°C
Halogen-free	Yes
Impact Strength	16 kJ/m ²
Mixing Ratio (weight)	100:22
Operating Temperature	-25 °C to +130 °C
Package Content packed in	bag
Pack Cont.	1450 ml
Pot Life	50 min. 5°C, 15 min. 23°C, 5 min. 23°C
ROHS compliant	Yes
Shelf Life	36 months
Shore Hardness D	56±5
Storage Temperature	+4 °C to +40 °C
Viscosity	4000 mPa*s, 5 °C (EN ISO 2555), 2000 mPa*s, 23 °C (EN ISO 2555)

