

Technische datasheet

Artikel Nummer
553-31254

TCGT12-4RD



Productgroep	Bedrukbare krimpkous, bedrukken met thermotransferprinter
Productfamilie	TCGT 3:1 standaard krimpkous
Materiaal	Polyolefine vernet (PO-X)
Kleur	rood (RD)
Aanbevolen tonerband	TTDTHOUT, TTRW, TT822OUT8
Breekspanning [Testmethode]	300 % [ASTM D638]
Certificering	C22.2 no. 198.1-99, MIL-STD-202H Method 215K
Gebruikstemperatuur - °C	-55 °C tot +135 °C
Hitteschoktest	4h/250°C
Hitteverouderingstest [Testmethode]	168h/175°C [ASTM D638]
Hoeveelheid per	karton
Inhoud	54 m
Krimpverhouding	3:1
Lengtekrimp	-15 % max. [ASTM D2671]
Maat bij uitlevering Ø D	12,0 mm
Minimale krimptemperatuur - °C	+90 °C
Na vrije krimp Ø d	4,0 mm
Printmethode	thermotransfer
Test bij lage temperatuur [Testmethode]	4h/-55°C [ASTM D2671]
Thermotransfer printer	TT431, TT4030DS, TT4030
Treksterkte testmethode	ASTM D638
Volumeweerstand [Testmethode]	10 ¹⁶ Ω cm [ASTM D257]
Wanddikte (WT)	0,68 mm
Waterabsorptie	0,20 %

RoHS

