


Technical data sheet

Article number:
553-71046

TULT24-8DS-3x16WH



Product Group	Shrinkable markers "Ladder Style", thermal transfer
Product Family	TULT DS – 3:1 Military and Electronics "Ladder Style"
Material	Polyolefin, cross-linked (PO-X)
Colour	White (WH)
Dielectric Strength [Test method]	20 kV/mm [ASTM D2671]
Elongation at break [Test method]	300 % [ASTM D638]
Flammability	UL 224 VW-1
Heat Aging Test [Test method]	168h/175°C [ASTM D638]
Heat Shock Test	4h/250°C
Longitudinal Change After Shrinkage [Test method]	-15% max. [ASTM D2671]
Low Temperature Test [Test method]	4h/-55°C [ASTM D2671]
Min. Shrink Temperature - °C	+90 °C
Operating Temperature	-55 °C to +135 °C
Package Content packed in	carton
Pack Cont.	750 pcs.
Print Method	thermal transfer print
Recommended Ribbon Type	TTDTHOUT
Recov. Ø d max.	8.0 mm
Shelf Life	24 months
Shrink Ratio	3:1
Specifications	MIL-STD-202H Method 215K
Storage conditions	50% relative humidity., The storage in the original packaging is recommended., Please avoid warehousing under impacts such as high humidity, heat and coldness.
Supplied Ø D min.	24.0 mm
Test Method Tensile Strength	ASTM D638
Thermal Transfer Printer	TT431, TT4030DS, TT4030
Volume Resistance [Test method]	10 ¹⁶ Ω cm [ASTM D257]

Wall (WT)	1.08 mm
-----------	---------

Water Absorption	0.20 %
------------------	--------

RoHS 

MIL