

## Technical data sheet

Article number:  
596-01029

**TAG01TD3**



<b>Product Group</b>	Asset identification label, thermal transfer
<b>Product Family</b>	Helatag 829
<b>Material</b>	Type 829, Polyester, white (829)
<b>Colour</b>	White gloss (GSWH)
<b>Adhesive</b>	Acrylic
<b>Adhesive strength</b>	Stainless steel: 710-750 N/m (FTM 1), Acrylates: 750-810 N/m (FTM 1), Polypropylene: 500-540 N/m (FTM 1), Glass: 730-770 N/m (FTM 1)
<b>Application Method</b>	The functionality and durability of the labels can be negatively affected if improperly processed or applied. All surfaces to be bonded must be clean, dry as well as free from dust and grease. Avoid touching the adhesive surface of the label as this could impair the application performance.
<b>Chem. Material Properties</b>	Excellent resistance to alcohol, fuel, cleaning solvents, butanol, ethyl- and and butylcellsolve solvent, battery acid.
<b>Curing Temperature</b>	from +10 °C
<b>Height (H)</b>	6.35 mm
<b>Initial tack [Test method]</b>	540 g/cm <sup>2</sup> [ASTM D2979]
<b>Labels per Row</b>	3 pcs.
<b>Material Durability</b>	2 years external weathering (central European climate). Colour might turn slightly yellow when exposed to direct sunlight.
<b>Mech. material properties</b>	Adhesive suitable for critical surfaces.
<b>Operating Temperature</b>	-40 °C to +150 °C
<b>Package Content packed in</b>	reel
<b>Pack Cont.</b>	7500 pcs.
<b>Print Method</b>	thermal transfer print
<b>Recommended Ribbon Type</b>	TT822OUT
<b>Shear strength [Test method]</b>	50 h [FINAT FTM 8]
<b>Storage conditions</b>	50% relative humidity., The storage in the original packaging is recommended., Please avoid warehousing under impacts such as high humidity, heat and coldness.
<b>Storage Temperature</b>	+21 °C
<b>Thermal Transfer Printer</b>	TT431, TT4030

Thickness of Foil [Test method]	50 µm [ASTM D3652]
Width of Liner (WL)	89.00 mm
Width (W)	25.40 mm

