

## **Technical data sheet**

## Article number: 596-12261

Package Content packed in

**Recommended Ribbon Type** 

**Shear strength [Test method]** 

Pack Cont.

**Print Method** 

**Storage conditions** 

**Storage Temperature** 

**Thermal Transfer Printer** 

**TAG43-41TD1** 



Product Group	Labels for IT ties and IMP plates, thermal transfer
Product Family	Helatag 892
Material	Type 892, Vinyl, white (892)
Colour	White (WH)
Adhesive	Acrylic
Adhesive strength	Stainless steel: 920-980 N/m (ASTM D903), Acrylates: 1390-1490 N/m (ASTM D903), Polypropylene: 545-610 N/m (ASTM D903), Glass: 1300-1380 N/m (ASTM D903)
Application Method	The functionality and durability of the labels can be negatively affected if improperly processed or applied. All surfaces to be bonded must be clean, dry as well as free from dust and grease. Avoid touching the adhesive surface of the label as this could impair the application performance.
Chem. Material Properties	Good resistance against water, oils and most solvents.
Curing Temperature	from 0 °C
Height (H)	41.00 mm
Initial tack [Test method]	610 g/cm² [ASTM D2979-71]
Labels per Row	1 pc.
Material Durability	3 years external weathering (central European climate)
Mech. material properties	Permanent adhesive, suitable for critical surfaces like low energy surfaces.
Operating Temperature	-40 °C to +80 °C

50% relative humidity., The storage in the original packaging is recommended., Please avoid

warehousing under impacts such as high humidity, heat and coldness.

reel

1000 pcs.

TT822OUT

+21 °C

thermal transfer print

5 h [ASTM D3654]

TT431, TT4030



Thickness of Foil [Test method]	83 μm [ASTM D3652-83]
Width of Liner (WL)	50.00 mm
Width (W)	43.00 mm

**RoHS**