


## **Technical data sheet**

## Article number: 597-65202

## ATWS5-A1D



Product Group	Warning signs (DIN4844 and BGV A8)
Product Family	HELASIGN, Material 150
Material	Type 150, Vinyl (150)
Colour	Yellow (YE)

Adhesive strength  Stainless steel: 15-19 N/25 mm (FTM 1)  The functionality and durability of the labels can be negatively affected if improperly processed or applied. All surfaces to be bonded must be clean, dry as well as free from dust and grease. Avoid touching the adhesive surface of the label as this could impair the application performance.  Chem. Material Properties  Resistant to oils, water and solvents; flame-retarding  Curing Temperature  from +10 °C  T4.00 mm  Initial tack [Test method]  110 g/cm² [ASTM D2979-71]
Application Method  The functionality and durability of the labels can be negatively affected if improperly processed or applied. All surfaces to be bonded must be clean, dry as well as free from dust and grease. Avoid touching the adhesive surface of the label as this could impair the application performance.  Chem. Material Properties  Resistant to oils, water and solvents; flame-retarding  Curing Temperature  from +10 °C  Height (H)  74.00 mm
Application Method  processed or applied. All surfaces to be bonded must be clean, dry as well as free from dust and grease. Avoid touching the adhesive surface of the label as this could impair the application performance.  Chem. Material Properties  Resistant to oils, water and solvents; flame-retarding  Curing Temperature  from +10 °C  Height (H)  74.00 mm
Curing Temperature from +10 °C Height (H) 74.00 mm
<b>Height (H)</b> 74.00 mm
g ty
Initial tack [Test method] 110 g/cm² [ASTM D2979-71]
y. a
Labels per Sheet 1 pc.
Operating Temperature -40 °C to +80 °C
Package Content packed in pack
Pack Cont. 10 pcs.
Peel strength [Test method] 550 N/m [PSTC 7]
Self adhesive (Yes/No) Yes
Shear strength [Test method] 120 h [FINAT FTM 7]
<b>Storage conditions</b> 50% relative humidity., The storage in the original packaging is recommended., Please awarehousing under impacts such as high humidity, heat and coldness.
Thickness of Foil [Test method] 80 μm [ASTM D3652-83]
Width of Liner (WL) 74.00 mm
<b>Width (W)</b> 210.00 mm

**RoHS**